



ARDEX TLT 700™

Multi-Purpose Construction Adhesive and Sealant

Sticks to virtually anything...even under water

Extremely versatile - Bonds a wide range of materials including glass, metal, wood, ceramics and plastic

Ideal for minor repair applications, even under water

Available in white

High bond strength

Use to fill movement joints

Interior and exterior walls and floors

Highly flexible

Neutral curing system - Free of solvents, water and isocyanates

Can be painted

Shrinkage free drying

Single component elastomeric hybrid

ARDEX Americas
400 Ardex Park Drive
Aliquippa, PA 15001 USA
Tel: 724-203-5000
888-512-7339
www.ardexamericas.com

ARDEX TLT 700™

Multi-Purpose Construction Adhesive and Sealant

Description

ARDEX TLT 700™ is a one-component, high modulus, mildew resistant multi-purpose elastomeric hybrid adhesive and neutral curing sealant that hardens in reaction with moisture. ARDEX TLT 700 is extremely flexible with excellent bond strength, making it suitable for a wide range of applications. It is ideal for replacing tiles or for use as a general shower, kitchen and bathroom repair adhesive and sealant for fitting accessories such as soap holders. ARDEX TLT 700 is shrinkage free and can be used to fill movement joints. Use on interior or exterior walls and floors. ARDEX TLT 700 is ideal for bonding most construction materials, including glass, tiles, ceramics, wood, plastic and metal.

ARDEX TLT 700 can be used in underwater applications, either applied to the immersed substrate or to the item to be affixed, making it ideal when minor repairs and alterations need to be carried out in fountains or other wet areas. ARDEX TLT 700 is intended for minor, temporary tile repairs in pools, such as re-affixing tiles that release while a pool is filled and until such time that the pool is drained for annual closing or maintenance. ARDEX TLT 700 is not intended for use as an exposed surface within a pool, such as in joints, nor is it intended for permanent installation of pool tiles.

Use For

- Minor tile repairs
- Attaching bathroom and shower accessories and door handles
- Virtually any repair

Bonds To

Refer to the manufacturer of the item being affixed for acceptable substrates.

ARDEX TLT 700 bonds to concrete, well-bonded cementitious underlayments, APA grade underlayment plywood (untreated), radiant-heated subfloors where temperatures do not exceed 85°F (29.4°C), gypsum drywall panels, ceramic tiles, plastic, metal, select waterproofing membranes, polystyrene foam and fiberglass*. Please note that all substrates must be sound, solid and well bonded.

*Fiberglass substrates, whether or not the glaze is roughened mechanically, are suitable only for minor repairs, especially in submerged applications.

Preparation

Refer to the manufacturer of the item being affixed for specific recommendations.

Acceptable installation temperatures range from 50°F (10°C) to 85°F (29°C).

Substrate must be sound, smooth and flat. Ensure that the substrate is solid and fixed securely to provide a rigid base free of undue flex. All loose wood must be re-nailed to create a sound surface. Patching and/or leveling materials must have a minimum compressive strength of 3,000 psi.

Substrate must be clean and free of excess moisture and alkali. Mechanically remove dirt, wax, grease, paints, oils, sealers, curing compounds and all foreign matter that would interfere with proper adhesion. Please note that when removing existing flooring, any asbestos-containing materials should be handled and disposed of in accordance with applicable federal, state and local regulations.

Dimensional Stability of Flooring Structures

Some floor coverings may grow or shrink as a result of acclimation, handling and/or how the product was manufactured. Install representative test areas to determine the suitability of ARDEX TLT 700 to resist any dimensional change. Please note that ARDEX cannot be held responsible for installation issues caused by dimensional changes in flooring structures. Please also note that ARDEX TLT 700 is recommended only for minor repairs.

Installation

Refer to the manufacturer of the item being affixed for specific instructions.

Apply ARDEX TLT 700 in strips to the substrate or to the item to be affixed. Allow a maximum distance of 9" - 11" (22 - 28 cm) between glue points. Set the item to be affixed immediately into the wet adhesive. Objects that are heavy enough to sag should be supported until ARDEX TLT 700 reaches its full cure.

Do not apply more adhesive than can be covered within 20 minutes (50% relative humidity). ARDEX TLT 700 will start to skin over within 20 minutes, depending on temperature and humidity. As this material reacts with moisture, please note that the skin will develop faster in higher humidity environments. If the adhesive dries or skins over, it must be scraped up, and fresh adhesive needs to be applied.

Adhesive must set a minimum of 24 hours before receiving traffic. Lower humidity levels and impervious substrates will need extra dry time.

Cleanup

Remove wet adhesive residue with a clean, white cloth dampened with soapy water. Dried adhesive must be scraped with a blade for removal.

Notes

FOR PROFESSIONAL USE ONLY.

As always, ARDEX recommends conducting an adequate number of test areas to determine the suitability of the product for its intended use. This is especially important for applications where the ARDEX TLT 700 will be painted and for submerged applications. The long-term stability of underwater applications may vary, depending on application.

Dispose of container and residue in accordance with federal, state and local waste disposal regulations. Do not flush material down drains.

Precautions

Carefully read and follow all precautions and warnings on the product label. For complete safety information, please refer to the Material Safety Data Sheet (MSDS) available at www.ardexamericas.com.

Technical Data According to ARDEX Quality Standards

All data based on 1/4" (6.35 mm) bead installed at 77°F (25°C) and 50% relative humidity. Physical properties are typical values and not specifications.

Material Base:	Silyl-terminated Polyether (hybrid) Elastomeric
Colors:	White
Storage Conditions:	40 - 90°F (5 - 32°C). Max. 50% relative humidity. Do not freeze or expose to moisture.
Skinning Time:	20 minutes
Curing Time:	1/8" per 24 hours
Operating Temperature:	-75 to 220°F
Practical Expansion:	25%
Coverage per Package:	1/4" (6.35 mm) Bead 32 linear ft. (9.75 linear M) 1/8" (3.18 mm) Bead 64 linear ft. (19.5 linear M)
Hardness Shore A:	46
Tensile Adhesion Strength:	225 psi
Warranty:	ARDEX L.P. Standard Limited 1-Year Warranty. Failure to follow written directions will void the warranty. For complete warranty details, please visit www.ardexamericas.com .
Shelf Life:	18 months
VOC:	18 g/L
Packaging:	10.1 oz. Cartridge

© 2021 ARDEX, L.P. All rights reserved. Content updated 04-19-2021. Published 04-21-2021. Supersedes all previous versions. Check www.ardexamericas.com for most recent version and for technical updates, which may supersede the information herein. AT388

For easy-to-use ARDEX Product Calculators and Product Information On the Go, download the ARDEX App at the iTunes Store or Google Play.

Visit www.youtube.com/ARDEX101 to watch our product demonstration videos.



ARDEX Americas
400 Ardex Park Drive
Aliquippa, PA 15001 USA
Tel: 724-203-5000
888-512-7339
www.ardexamericas.com