



# Crack Suppression Kit

DS-648.0-0310



## 1. PRODUCT NAME

LATICRETE® Crack Suppression Kit

## 2. MANUFACTURER

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany, CT 06524-3423 USA

Telephone: +1.203.393.0010, ext. 235

Toll Free: 1.800.243.4788, ext. 235

Fax: +1.203.393.1684

Internet: [www.laticrete.com](http://www.laticrete.com)

## 3. PRODUCT DESCRIPTION

LATICRETE Crack Suppression Kit consists of liquid rubber and reinforcing fabric packaged for convenient individual treatment of substrate cracks. When cured, it forms a highly flexible membrane that reduces or eliminates crack transmission in tile or stone work.

### Uses

- Wherever hairline cracking or “spiderwebbing” occurs in the substrate, including interior or exterior floors and walls.
- For use over shrinkage and other non-structural cracks up to 1/8" (3 mm) wide.
- Ideal for suspended or on grade concrete slabs in malls, lobbies and residential applications under ceramic tile and stone installed by the thin-bed or bonded thick-bed methods.
- Cover joints in plywood, cement backer boards, and concrete masonry on floors and walls.
- Also use over concrete floors and underlayments containing radiant heating.

### Advantages

- Reduces crack transmission in ceramic tile, thin brick and stone.
- Contains Microban® anti-microbial protection to inhibit the growth of stain causing mold and mildew in the membrane.
- Thin—adds no appreciable thickness to floor construction: install tile with LATICRETE Latex Thin-Set Mortar directly to cured membrane.
- Easy to Apply—goes on quickly with paint brush or roller—no

mixing or special equipment required.

- Fast Cure—ready in a few hours to receive ceramic tile and stone.
- Easy Cleanup—cleans with water while fresh.
- Safe—no solvents or harsh fumes, non-flammable.
- “Extra Heavy Service” rating per TCNA performance levels (RE: ASTM C627 Robinson Floor Test).

### Suitable Substrates

- Concrete
- Mortar beds, renders
- Concrete masonry
- Exterior glue plywood\*
- Cement backer board\*\*
- Cement terrazzo\*\*\*
- Ceramic Tile and Stone\*\*\*

\* Interior applications only.

\*\* Consult cement backer board manufacturer for specific installation recommendations and to verify acceptability for exterior use.

\*\*\* If skim-coated with a LATICRETE® Latex Thin-Set Mortar

### Packaging

Each LATICRETE Crack Suppression Kit contains:

- 2 gal (7.6 l) jug of LATICRETE Crack Suppression Kit Liquid
- 15" wide x 75 ft long (38 cm x 23 m) roll of LATICRETE Reinforcing Fabric

### Coverage

Approximately 75 linear ft (23 m)

### Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for two (2) years if stored at temperatures >32°F (0°C) and <110°F (43°C).

### Limitations

- DO NOT use over expansion joints, structural cracks or areas with differential vertical movement.
- LATICRETE Crack Suppression Kit is not a waterproofing membrane. When a waterproofing membrane is required, use a LATICRETE Waterproofing Membrane (see Section 10 FILING SYSTEMS).
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproofing membranes.
- Apply to surfaces above 45°F (7°C). Maintain a constant temperature greater than 45°F (7°C) for 24 hours after installation.
- Not intended as a wearing surface—must be covered with tile, or other traffic bearing material
- DO NOT bond to particle board, luan, Masonite® or hardwood surfaces.

## Cautions

- For white and light colored marbles use LATICRETE® 220 Marble & Granite Mortar WHITE.
- During cold weather, protect finished work from traffic until fully cured.
- For green, resin-backed agglomerates and moisture sensitive marbles, use LATAPOXY® 300 Adhesive. Refer to Data Sheet 633.o.
- Protect freshly installed membrane from water exposure.

## 4. TECHNICAL DATA

### VOC/LEED Product Information



This product has been GREENGUARD Indoor Air Quality Certified® by the GREENGUARD Environmental Institute under the GREENGUARD Standard for Low Emitting Products in finished form.

Total VOC Content pounds/gallon (grams/liter) of product in unused form is 0.02 lb/gal (2.39 g/l).

### Performance properties

Meets ANSI A118.12 specification.

Physical Properties	Test Method	LATICRETE Crack Suppression Kit	ANSI A118.12
System Crack Resistance	ANSI A118.12 5.4	Pass at 1/8" (3 mm)	Pass at 1/8" (3 mm)
Elongation	ASTM D751-89; 17.1	20-30%	20-30%
Breaking Strength (Cut Strip Method)	ASTM D751-89; 16.1	1700-1900 psi (11.72-13.10 MPa)	1700-1900 psi (11.72-13.10 MPa)
Nominal Dry Thickness	LIL 1013-92	0.020" (0.51 mm)	0.020" (0.51 mm)
28 day Quarry/Concrete Shear Strength	ANSI A118.12 5.1.5	125-175 psi (0.86-1.6 MPa)	50 psi (0.34 MPa)
Point Load	ANSI A118.12 5.2	3200-3700 lb/f (14-16 kN)	1000 lbs/f (4.4 kN)

Data from report 031219-P-182-176.

Specifications are subject to change without notification. Results shown are typical but reflect test procedure used. Actual field performance will depend on the type of tile/stone used, installation methods and site conditions.

## 5. INSTALLATION

### Inspection

**IMPORTANT NOTE:** Verify that all cracks to be treated are caused by shrinkage due to concrete curing and are not structural in nature (typically caused by inadequate substrate design and/or construction for load conditions). Do not use LATICRETE Crack Suppression Kit over structural cracks or other areas with differential vertical movement.

### Surface Preparation

All surfaces should be between 45°F (7°C) and 90°F (32°C) and structurally sound, clean and free of all dirt, oil, grease, paint, concrete sealers or curing compounds and laitance. Rough or uneven concrete surfaces should be made smooth with a LATICRETE Underlayment to provide a wood float or better finish. Do not level with gypsum or asphalt-based products. Dry, dusty concrete slabs or masonry should be cleaned, dampened and excess water swept off. Installation may be made on a damp surface. New concrete slabs shall be damp cured and a minimum of 14 days old before application (see membrane instructions WPAF.5 for additional information). All slabs must be plumb and true to within 1/4" (6 mm) in 10 ft (3 m). Existing ceramic tile and stone installations should be thoroughly cleaned and skim coated with a LATICRETE Latex Fortified Thin-Set Mortar.

1. Installer must verify that deflection under all live, dead and impact loads of interior plywood floors does not exceed industry standards of L/360 for ceramic tile and brick or L/480 for stone installations where L=span length.

2. Minimum construction for interior plywood floors.  
**SUBFLOOR:** 5/8" (15 mm) thick exterior glue plywood, either plain with all sheet edges blocked or tongue and groove, over bridged joints spaced 16" (400 mm) o.c. maximum; fasten plywood 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. along intermediate supports with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) between sheet ends and 1/4" (6 mm) between sheets edges; all sheet ends must be supported by a framing member; glue sheets to joints with construction adhesive

**UNDERLAYMENT:** 5/8" (15 mm) thick exterior glue plywood fastened 6" (150 mm) o.c. along sheet ends and 8" (200 mm) o.c. in the panel field (both directions) with 8d ring-shank, coated or hot dip galvanized nails (or screws); allow 1/8" (3 mm) to 1/4" (6 mm) between sheets and 1/4" (6 mm) between sheet edges and any abutting surfaces; offset underlayment joints from joints in subfloor and stagger joints between sheet ends; glue underlayment to subfloor with construction adhesive. Refer to Technical Data Sheet 152 Bonding Ceramic Tile, Stone or Brick Over Wood Floors for complete details.

## Application

### For Hairline and Shrinkage Cracks

Use a wide brush/roller to cover crack to be treated with a liberal coat of LATICRETE Crack Suppression Liquid at least 17" (43 cm) wide. Imbed 15" (38 cm) wide LATICRETE Reinforcing Fabric while liquid is still wet. Press firmly with brush/roller to allow complete "bleed through" of liquid. Liberally apply an additional coat of liquid to cover/saturate fabric. Let dry 1-3 hours. Install tile using a LATICRETE Polymer Fortified Thin-Set Mortar.

### For Cold and Saw Cut Joints

Use a roller to cover the joint to be treated with a liberal coat LATICRETE Crack Suppression Liquid a minimum of one tile width on each side of the joint. The width should be a minimum of three times the width of the tile. Embed the 15" (38 cm) wide LATICRETE Reinforcing Fabric while the liquid is still wet. Press firmly with a brush/roller to allow complete "bleed through" of the liquid. Lap the fabric at all seams. Liberally apply an additional coat of liquid to cover/saturate the fabric. Let dry 1-3 hours. Install tile using a LATICRETE Polymer Fortified Thin-Set Mortar. Treat closest grout joint to cold or saw cut joint with LATICRETE Latasil.

## 6. AVAILABILITY AND COST

### Availability

LATICRETE and LATAPOXY materials are available worldwide.

### For Distributor information, call:

Toll Free: 1.800.243.4788  
Telephone: +1.203.393.0010

For on-line Distributor information, visit LATICRETE at [www.laticrete.com](http://www.laticrete.com).

### Cost

Contact a LATICRETE/LATAPOXY Distributor in your area.

## 7. WARRANTY

See 10. FILING SYSTEM  
DS 230.13 LATICRETE Product Warranty

## 8. MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY products require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers (e.g. caulking and expansion joints).

## 9. TECHNICAL SERVICES

### Technical assistance

Information is available by calling the LATICRETE Technical Service Hotline (hours 8:00 AM to 5:30 PM EST):

Toll Free: 1.800.243.4788, ext. 235  
Telephone: +1.203.393.0010, ext. 235  
Fax: +1.203.393.1948

### Technical and safety literature

To acquire technical and safety literature, please visit our website at [www.laticrete.com](http://www.laticrete.com).

## 10. FILING SYSTEM

Additional product information is available on our website at [www.laticrete.com](http://www.laticrete.com). The following is a list of related documents:

DS 230.13 LATICRETE® Product Warranty  
DS 236.0: LATICRETE 9235 Waterproofing Membrane  
DS 297.0: LATICRETE 220 Marble & Granite Mortar  
DS WPAF.5: Installation of LATICRETE Membranes  
DS 633.0: LATAPOXY® 300 Adhesive  
DS 6200.1: LATICRETE Latasil™  
TDS 152: Bonding Ceramic Tile, Stone or Brick Over Wood Floors  
DS 663.0: LATICRETE Hydro Ban™

---

LATICRETE International, Inc.  
One LATICRETE Park North, Bethany, CT 06524-3423 USA • 1.800.243.4788 • +1.203.393.0010 • [www.laticrete.com](http://www.laticrete.com)

©2010 LATICRETE International, Inc.  
LATICRETE, LATAPOXY, SPECTRALOCK and the  logo are Registered Trademarks of LATICRETE International, Inc.

Masonite is a registered trademark of Masonite International Corporation.  
GREENGUARD Indoor Air Quality is a registered trademark of the GREENGUARD Environmental Institute.  
Microban is a registered trademark of Microban Products Company.

**DS-648.0-0310**